

Uniclass	EPIC
L522:P* Cl/SFB	E321:X*
(47)	Rn6



# SUNLITE®

*Multi-Wall Polycarbonate Sheet*



Glazing



Construction



DIY



Advertising



Agriculture

## ► Introduction

SUNLITE sheets combine the characteristic strength of polycarbonate with superior insulation. This combination yields a strong, insulating, lightweight and attractive sheet for varied roofing, cladding, and glazing. SUNLITE provides solutions for markets as diverse as construction, agriculture, industry, DIY and advertising.

## ► Features at a Glance

- **New:** X-Lite structure for improved overall mechanical performance
- Energy saving
- Excellent impact resistance
- Lightweight
- High light transmission
- Weather and UV resistant benefits
- Superb thermal insulation - Energy saving
- Blocks virtually all UV radiation
- Easy to handle and install
- High fire performance rating

## ► Applications

- Conservatories
- Skylights
- Signs
- Covered Walkways
- Industrial Roofing and Glazing
- Do-It-Yourself (DIY)
- Swimming Pools
- Greenhouses



## ► Typical Physical Properties

Property	(Method)	Conditions	Units	Value
Density	(D-1505)		g/cm <sup>3</sup>	1.2
Heat Deflection Temperature	(D-648)	Load: 1.82 MP	°C	130
Service Temperature - Short Term			°C	-50 to +120
Service Temperature - Long Term			°C	-50 to +100
Coefficient of Linear Thermal Expansion	(D-696)		10 <sup>-5</sup> /°C	6.5
Tensile Strength at Yield	(D-638)	10 mm/min	MPa	62
Elongation at Break	(D-638)	10 mm/min	%	>80
Impact Falling Dart	(ISO 6603/1)		J	40 - 400

## ► Flammability

SUNLITE complies with international fire resistance standards, as presented by the results in the following table :

Method	Classification*
BS 476/7	Class 1
DIN 4102	B-1
NSP 92501	M-1, M-2
ASTM D-635	CC-1 (SUNLITE® SL)
ASTM E-84	Class A

\* For additional information please consult your SUNLITE distributor.

## ► Colors

### Standard

Clear, Bronze, Opal, Solar Metallic.

### Special Transparent


Sky Blue, Sea Green.

### ML (Multi-Layered)

Bronze/Opal, Solar Guard.

Structure	% Light Transmission by Colours										
	Standard Colours							Multi-Layer		New DC	
	Clear	Bronze	Solar Grey	White Opal	Opal WD	Solar Metallic Grey	Solar Ice	Bronze/Opal	Solar Guard	CL	AG
Twin Wall 4 mm	82%	35%	25%	30%		30%					
Twin Wall 4.5 mm	82%	35%	25%	30%		30%					
Twin Wall 6 mm	80%	35%	25%	20%		30%					
Twin Wall 8 mm	80%	35%	25%	35%		25%				45%	45%
Twin Wall 10 mm	79%	35%	25%	30%		25%				45%	45%
Triple Wall 8 mm	76%	35%		48%		25%					
Triple Wall 10 mm	76%	35%		48%		25%					
Triple Wall 16 mm	76%	35%	25%		48%	25%		20%	10%		
X-Lite 10 mm	63%										
X-Lite 16 mm	60%	25%			38%	18%	15%				30%
X-Lite 25 mm	60%	25%			20%	20%	15%	10%	5%		20%
X-Lite 32 mm	58%	20%			20%	20%	15%	10%	5%		20%
X-Lite 35 mm	57%	20%			20%	20%	15%	10%	5%		20%

## ► Standard Dimensions

Structure	Thickness mm	Area Weight kg/m <sup>2</sup>	U-value W/m <sup>2</sup> °K	Standard Sheet Width (mm)								
				980	1050	1220	1250	1600	1800	1830	2100	
Twin-Wall 	4	0.8	3.8	✓	✓	✓	✓				✓	✓
	4.5	1.0	3.7	✓	✓						✓	✓
	6	1.3	3.5	✓	✓	✓	✓				✓	✓
	8	1.5	3.3	✓	✓	✓	✓				✓	✓
	10	1.7	3.0	✓	✓	✓	✓				✓	✓
Triple-Wall 	8	1.7	2.9								✓	✓
	10	2.0	2.7								✓	✓
	16	2.7	2.3	✓	✓	✓	✓	✓	✓	✓	✓	✓
X-Lite 	10	1.9	2.6								✓	✓
	16	2.5	2.1	✓	✓	✓	✓	✓	✓	✓	✓	✓
	25	3.4	1.7	✓	✓	✓	✓	✓	✓	✓	✓	✓
	32	3.7	1.6	✓	✓	✓	✓	✓	✓	✓	✓	✓
	35	3.9	1.5	✓	✓			✓	✓	✓	✓	✓

## ► Additional SUNLITE® Products

- Solar Control™ *Breaking the penetrating heat/light ratio*
- SUNLITE® UV2 *UV protection on two sides*
- SUNLITE® Plus *Clear SUNLITE with anti-condensation treatment*
- SUNLITE® CL *With advanced heat filtering for architectural applications*
- SUNLITE® AG *With special coloring and anti-condensation*

Inasmuch as PALRAM Industries has no control over the use to which others may put the material, it does not guarantee that the same results as those described herein will be obtained. Each user of the material should make his own tests to determine the material's suitability for his own particular use. Statements concerning possible or suggested uses of the materials described herein are not to be construed as constituting a license under any PALRAM Industries patent covering such use or as recommendations for use of such materials in the infringement of any patent. PALRAM Industries or its distributors cannot be held responsible for any losses incurred through incorrect installation of the material. In accordance with our company policy of continual product development you are advised to check with your local PALRAM Industries supplier to ensure that you have obtained the most up to date information.

Europe  
UK  
Israel  
USA  
Australia  
Far East



### EUROPE

**PALRAM EUROPE LTD. PALRAM UK**

Tel ► (44) 1302 380 777 Tel ► (44) 1302 380 738

Fax ► (44) 1302 380 788 Fax ► (44) 1302 380 739

sales.europe@palram.com sales.uk@palram.com

### ISRAEL

**PALRAM ISRAEL LTD.**

Tel ► (972) 4 8459 900

Fax ► (972) 4 8459 980

palram@palram.com

### USA

**PALRAM AMERICAS**

Tel ► 610 285 9918

Fax ► 610 285 9928

palramamericas@palram.com



[www.palram.com](http://www.palram.com)